



# LL20FS020 LL20FA020

## LINEAR LOW DENSITY POLYETHYLENE FILM EXTRUSION GRADE

This is butene based Linear Low Density Polyethylene grade with Optimum level of Antioxidants and is designed for good processing on Blown and Cast Film lines with balanced mechanical & optical Properties

**LL20FS020:** With Slip & Anti block

**LL20FA020:** Without Slip & Anti block

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	2.0
Density (23°C)	ASTM D 1505	g/cm <sup>3</sup>	0.918
Tensile Strength at Break (MD / TD)	ASTM D 882	Kg/cm <sup>3</sup>	300 / 200
Elongation at Break (MD / TD)	ASTM D 882	%	800 / 950
Tear Strength (MD / TD)	ASTM D 1922	g/μm	2.5 / 7.5
Dar Drop Impact (F-50)	ASTM D 1922	g/ μm	2.1
Haze	ASTM D 1003	%	16

\* Typical characteristics and not to be taken as specifications

\*\* Typical values of 40 μ film made with 1.8 mm die gap & 2.25 BUR on LL20FA020

### APPLICATIONS:

Blown & Cast Films. For Co extrusion, Lamination, Mulch films for Agriculture, Shopping bags, Liners, Protection films, Bubble wrap films & other packaging films.

### Regulatory Information

• Meets the requirement stipulated in standard IS: 10146 on “Specification for Polyethylene for safe use in contact with foodstuff, pharmaceutical, and drinking water”. It also conforms to the positive list of constituents as prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177,1520, Olefin polymers

### Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

**Reliance Industries Limited**, Product Application Research Centre (PARC)

Reliance Industries Limited, Baroda Complex, P.O.Petrochemicals, District Vadodara: Pin 391346, Gujarat, India

E-mail: [polymer\\_patsupport@ril.com](mailto:polymer_patsupport@ril.com) Website: [www.ril.com](http://www.ril.com)

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.