



1003FA20

LOW DENSITY POLYETHYLENE HEAVY DUTY FILM APPLICATIONS

1003FA20 is a film grade Low Density Polyethylene (LDPE) produced by high pressure autoclave process. It has been specially designed for the production of film with good environmental stress crack resistance, mechanical and impact resistance. Film produced from this grade is ideally suitable for heavy duty applications.

TYPICAL CHARACTERISTICS*

Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	0.3
Density (@ 23°C)	ASTM D 1505	g/cm ³	0.920
Tensile Strength at Break (MD/TD)	ASTM D 882	MPa	25/22
Elongation @ Break (MD/TD)	ASTM D 882	%	300/550
Dart Drop Impact (F-50)	ASTM D 1709/A	g/μm	5.0

*Typical characteristics are not to be taken as specifications.

**Typical Values (Mechanical) with 40 μ film made with 1 mm die gap & 2.0 BUR.

APPLICATIONS :

Heavy Duty / Shrink Film, UV Film, W&C Compound, Agri-Film

Regulatory Information

Meets the requirement stipulated in standard IS: 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to positive list of constituents as prescribed in IS: 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21.177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance industries Limited, Product Application and Research Centre ,Swastik Mill Compound, V.N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of December 2012