



X24065

LINEAR LOW DENSITY POLYETHYLENE Grade for Medium Voltage XLPE Cable Compounds

Relene X24065, is a Butene comonomer based Linear Low Density Polyethylene. This grade is designed for XLPE cable compounds. It offers superior Processability, ESCR and Abrasion resistance.

TYPICAL CHARACTERISTICS*

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE**
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	6.4
Density (@ 23°C)	ASTM D 1505	g/cc	0.924
Tensile Strength at Yield	ASTM D 638	MPa	11
Tensile Strength at Break	ASTM D 638	MPa	15
Elongation @ Yield	ASTM D 638	%	17
Elongation @ Break	ASTM D 638	%	> 600
Flexural Modulus	ASTM D 790	MPa	260
Hardness	ASTM D 2240	Shore D	53

*Typical characteristics are not to be taken as specifications.

**Typical Values (Mechanical) with 3.2 mm thick Injection Molded Specimen

APPLICATIONS :

Medium Voltage XLPE Cable Compounds

Regulatory Information

Meets the requirement stipulated in standard IS: 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to positive list of constituents as prescribed in IS: 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21.177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance industries Limited, Product & Application Technology Group ,Swastik Mill Compound, V.N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of January 2009